



FBPE10000-8-11MP draft

Polymer Composition: LLDPE Blend
Shape: Fibrillated Yarn
Number of cuts 8 / cm

Test Data:

Test	Method	Typical Value	Unit
Mass density	ASTM D1907-07;	10,000	denier
Mass density	ASTM D1907-07;	11,000	dtex
Thickness	ASTM D 3218-07;	115	Microns
Width	ASTM D 3218-07;	11	mm
Fastness to Weathering	ISO 75220	5	Grey Scale
Tensile Strength at Break	ASTM D 2256		lbf
Elongation at break	ASTM D 2256		%

Each lot of this Product is tested by an independent ISO/IEC 17025 accredited lab for the correct amount of UV, heat and process stabilizers.

APT / Polytex USA
237 Boling Industrial Way
Calhoun, GA 30701
+1 706 229 4433
info@polytex-usa.com
www.polytex-usa.com