



MFPE350RB

Polymer Composition: LLDPE Blend
Shape: Diamond
Filament count: 6 per Filament

Test Data:

Test	Method	Typical Value	Unit
Mass density (per Filament / Bundle)	ASTM D1907-07;	2000 / 12000	dtex
Mass density (per Filament / Bundle)	ASTM D1907-07;	1800 / 10800	denier
Thickness	ASTM D 3218-07;	350	Microns
Width	ASTM D 3218-07;	1.1	mm
Fastness to Weathering	ISO 75220	5	Grey Scale
Tensile Strength at Break (per Filament)	ASTM D 2256	4.2	lbf
Elongation at break (per Filament)	ASTM D 2256	100	%
Tensile Strength at Break (per 6 Filaments)	ASTM D 2256	20.3	lbf
Elongation at break (per 6 Filaments)	ASTM D 2256	94	%

APT / Polytex USA
237 Boling Industrial Way
Calhoun, GA 30701
+1 706 229 4433
info@polytex-usa.com
www.polytex-usa.com