



FBPE8400-7-9P

Polymer Composition: LLDPE Blend
Shape: Fibrillated Yarn
Number of cuts 8 / cm

Test Data:

Test	Method	Typical Value	Unit
Mass density	ASTM D1907-07;	8400	denier
Mass density	ASTM D1907-07;	9300	dtex
Thickness	ASTM D 3218-07;	115	Microns
Width	ASTM D 3218-07;	9	mm
Fastness to Weathering	ISO 75220	5	Grey Scale
Tensile strength at Break	ASTM D 2256	17.0	Lbf
Elongation at Break	ASTM D 2256	45	%

Each lot of this Product is tested by an independent ISO/IEC 17025 accredited lab for the correct amount of UV, heat and process stabilizers.

APT / Polytex USA
237 Boling Industrial Way
Calhoun, GA 30701
+1 706 229 4433
info@polytex-usa.com
www.polytex-usa.com