



## MFPE200RE TXT

Polymer Composition: LLDPE Blend  
Shape: Rectangular / Texturized  
Filament count: 6 per Filament

### Test Data:

Test	Method	Typical Value	Unit
Mass density (per Filament / Bundle)	ASTM D1907-07;	2000 / 12000	dtex
Mass density (per Filament / Bundle)	ASTM D1907-07;	1800 / 10800	denier
Thickness	ASTM D 3218-07;	200	Microns
Width	ASTM D 3218-07;	1.1	mm
Fastness to Weathering	ISO 75220	5	Grey Scale
Bulk determined at 80°C for 10 Minutes	internal	14	%

Each lot of this Product is tested by an independent ISO/IEC 17025 accredited lab for the correct amount of UV, heat and process stabilizers.

APT / Polytex USA  
237 Boling Industrial Way  
Calhoun, GA 30701  
+1 706 229 4433  
[info@polytex-usa.com](mailto:info@polytex-usa.com)  
[www.polytex-usa.com](http://www.polytex-usa.com)

APT / Polytex USA  
237 Boling Industrial Way  
Calhoun, GA 30701  
+1 706 229 4433  
[info@polytex-usa.com](mailto:info@polytex-usa.com)  
[www.polytex-usa.com](http://www.polytex-usa.com)